


PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B32B 3/14, B65H 23/035, 23/32, 35/02, B29C 53/04		A1	(11) International Publication Number: WO 97/15442 (43) International Publication Date: 1 May 1997 (01.05.97)
(21) International Application Number: PCT/US96/17165 (22) International Filing Date: 22 October 1996 (22.10.96) (30) Priority Data: 08/547,059 23 October 1995 (23.10.95) US 08/722,286 9 October 1996 (09.10.96) US (71) Applicant: CLOPAY PLASTIC PRODUCTS COMPANY, INC. [US/US]; Suite 1600, 312 Walnut Street, Cincinnati, OH 45202 (US). (72) Inventors: MORTELLITE, Robert, M.; 64 West Hatt-Swank Road, Maineville, OH 45039 (US). MUSHABEN, Thomas, G.; 3696 Grovedale Place, Cincinnati, OH 45208 (US). PRESTON, Kevin, W.; 1842 Vanderbilt Drive, Loveland, OH 45140 (US). (74) Agents: JOSEPHIC, David, J. et al.; Wood, Herron & Evans, P.L.L., 2700 Carew Tower, Cincinnati, OH 45202 (US).			(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>

(54) Title: PRODUCT, APPARATUS AND PROCESS FOR STRIP LAMINATION OF A POLYMER FILM AND NONWOVEN OR WOVEN WEBS**(57) Abstract**

A product, apparatus and process for lamination of a sheet of polymer film (19) onto a sheet of light weight web material (4). An incoming sheet (4) of material is slit into narrow webs (9), which may be folded by a folding guide (13), and separated by use of turning bars (12) and guides (14). The narrow webs (9) then enter an embossing or lamination station (15). The lamination process joins the two sheets which are of different widths to allow the process to produce stock for different final products. The laminate (21) of folded webs (9) and polymer (19) may be slit and/or unfolded prior to being stored on a take-up reel (30).

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

- 1 -

**PRODUCT, APPARATUS AND PROCESS FOR STRIP LAMINATION OF
A POLYMER FILM AND NONWOVEN OR WOVEN WEBS**

Background of the Invention

This Application is a continuation in part of U.S. Patent Application Serial No. 08/547,059, filed October 23, 1995 (pending) entitled **APPARATUS AND PROCESS FOR STRIP LAMINATION OF A POLYMER FILM AND**
5 **NONWOVEN OR WOVEN WEBS.**

Processes of laminating polymer films over spaced narrow webs are known. Relevant patents regarding lamination of narrow spaced webs include U.S. Patent Nos. 3,477,126, 3,656,513 and 4,859,259.
10 The '126 patent discloses a method of making a strip conductor material where webs of aluminum, which are spaced apart on a roll, are unrolled and an extruder applies a layer of plastic material to one side of the webs. The wide extruded layer is later slit to form
15 individual aluminum webs with the plastic material covering one surface of the individual webs and

- 2 -

overhanging both sides. The '513 patent discloses a method of manufacturing strip material for fabricating container bodies wherein a single wide roll of cardboard is slit, skived and extrusion coated with plastic on both sides. The '513 patent shows turning bars for steering the individual cardboard strips into subsequent manufacturing processes after the webs have been slit and laminated. The '259 patent discloses a process and apparatus for fabricating re-closable plastic bags wherein a double set of interlocking closure strips are unrolled from a reel, the strips are separated and a polymer film is extruded onto the strips. The polymer film is then slit, folded around a folding apparatus and wound upon reels.

Processes of dynamically bonding thermoplastic films are also known. U.S. Patent No. 4,919,738 herein incorporated by reference teaches a method and apparatus for dynamically mechanically bonding laminate layers, including at least one thermoplastic layer, by a pressure biased nip and an opposed roller.

Summary of the Invention

The present invention is directed to a method and apparatus for laminating polymer to another

- 3 -

material where the polymer has a different width than the material to which it is laminated.

One aspect of the present invention is directed to process and apparatus for laminating a wide web of nonwoven with narrow strips of polymer.

Another aspect of the invention is directed to a process and apparatus to continuously perform web splitting, folding, , guiding and laminating steps in a single unit. A single wide web of nonwoven is slit, folded, spaced apart by a predetermined distance by the use of turning bars and steered into a subsequent lamination process. Depending on the spacing between folded webs, each strip of polymer may include a loose flap on either side which may be suitable for forming a barrier cuff in a diaper or other hygiene product. The spacing between folded webs determines the width of a loose polymer flap which is formed.

Yet another aspect of the invention is directed to a process and apparatus to continuously perform web splitting, separating, guiding and laminating steps in a single unit. A single wide web is slit, separated by the use of turning bars and steered into a subsequent lamination process.

- 4 -

This invention provides an apparatus and method of producing the laminate on high speed production machines at line speeds of about 300-1,200 feet per minute (fpm). It involves in-line slitting of a single wide web of material, turning, separating, and subsequently laminating the webs. More specifically, a web is unrolled from a wide roll of nonwoven material. The incoming web is slit into narrow webs by score slitting, shear slitting, razor slitting, laser, water jet slitting or ultrasonic slitting, the narrow webs, which may be folded at a folding plate, then move down the line to turning bars which are displaced one from the other by a desired web separation distance. The spaced webs are then guided to an embossing or laminating station where the spaced webs are fed through nip rollers to adhere molten or solid polymer to the webs. More specifically, the webs may be introduced into a nip of rollers for extrusion lamination with a polymer film or may be dynamically mechanically bonded to a solid polymer film. When laminating the nonwoven to a polymer extrudate, the extrudate is extruded into the nip at a temperature above its softening point to form a film. The compressive force between the webs and the extrudate at the nip is controlled to bond one surface of the web to

- 5 -

the film to form the laminate. The wide laminate layer is then slit and may be unfolded prior to winding on a take-up reel. . When laminating to a solid film of polymer the film may be slit and separated, as
5 described above, and then dynamically bonded to a wide nonwoven web.

Other benefits, advantages and objectives of this invention will be further understood with reference to the following detailed description.

10 Brief Description of the Drawings

FIG. 1 is a diagrammatic perspective view of an in-line apparatus for slitting, turning and separating a nonwoven web with subsequent extrusion laminating.

15 FIG. 2 is a diagrammatic perspective view of an in-line apparatus for slitting, folding, turning and spacing a nonwoven web with subsequent extrusion laminating.

FIG. 2A is a diagrammatic perspective view of a double folding apparatus of the present invention.

20 FIG. 3 is a schematic perspective view showing the combination turning bar and guiding mechanism.

25 FIG. 4 is a schematic perspective view of a folding bar used in the present invention.

- 6 -

FIG. 5 is a schematic perspective view of an unfolding bar used in the present invention.

FIG. 6 is a schematic perspective view of folded nonwoven webs after lamination to polymeric film.

FIG. 7 is a schematic perspective view of a single nonwoven strip after slitting of the polymeric film and after unfolding.

FIG. 8 is a diagrammatic perspective view of a folding apparatus of the present invention

FIG. 9 is a diagrammatic perspective view of an in-line apparatus for slitting a polymer sheet, turning and spacing the polymer strips for lamination with a wide web of nonwoven.

Detailed Description of the Drawings

It is a primary objective of this invention to provide a method and apparatus for forming a plurality of spaced laminated strips of nonwoven web material and polymer film on high speed production machinery. The laminate strips are characterized by being impervious to the passage of fluid by virtue of the polymer film while maintaining a soft feel on the fibrous web surface of the laminate. It is another objective of this invention to provide a method and

- 7 -

apparatus for forming a wide strip of nonwoven with a narrow strip of polymeric material laminated thereto. Another objective of the present invention is to provide a product having a wide strip of nonwoven with a narrow strip of polymeric material laminated thereto.

In a first embodiment of the present invention a non-woven web is used to provide an inexpensive waterproof laminate which has a soft hand. In another embodiment, an elastic fabric web is used to provide stretch qualities desired. In yet another embodiment, a polymer web may be laminated to the polymer film to provide a double polymer film laminate. Various degrees of vapor or air permeability may be achieved in the laminate, for instance, by providing mechanical microvoids.

In a preferred form, the laminate produced by the present invention has the desirable feature of soft feel to achieve utility in a number of applications including diapers, underpads, sanitary napkins or other products. In another form of the invention, the laminate of the present invention includes loose flaps of polymeric material which is suitable for use as a barrier cuff.

The polymer film is preferably a thermoplastic polymer that is processable into a film

- 8 -

for direct lamination by melt extrusion onto the nonwoven web in one embodiment. Suitable polymers for the film include polyethylene, polypropylene, poly(ethylene-butene), poly(ethylene-hexene),
5 poly(ethylene-octene), poly(ethylene-propylene), poly(styrene-butadiene-styrene), poly(styrene-isoprene-styrene), poly(styrene-ethylene-butylene-styrene), poly(ester-ether), poly(ether-amide), poly(ethylene-vinylacetate), poly(ethylene-methylacrylate),
10 poly(ethylene-acrylic acid), poly(ethylene-butylacrylate), polyurethane, poly(ethylene-propylene-diene), ethylene-propylene rubber. A new class of rubber-like polymers may also be employed and they are generally referred to herein as polyolefins produced
15 from single-site catalysts. The most preferred catalysts are known in the art as metallocene catalysts whereby ethylene, propylene, styrene and other olefins may be polymerized with butene, hexene, octene, etc., to provide elastomers suitable for use in accordance
20 with the principles of this invention, such as poly(ethylene-butene), poly(ethylene-hexene), poly(ethylene-octene), poly(ethylene-propylene) and/or polyolefin terpolymers thereof.

Suitable thermoplastic polymers may be
25 biodegradable or environmentally degradable. A number

- 9 -

of bi degradable therm plastic polymers suitable in the practice of the invention are of the normally-solid oxyalkanoyl polymers or dialkanoyl polymers represented by poly(caprolactone) or poly(ethylene adipate);

5 polysaccharides or modified polysaccharides such as starch-resin compositions that may be film-formed. Suitable thermoplastic polymers that may also be environmentally degradable include polyolefin based polymers that may be film-formed into water insoluble

10 and impermeable films for use as barrier materials in the manufacture of many useful articles such as diapers, underpads, packaging, drapes and the like. The olefin based polymers include the most common ethylene or propylene based polymers such as

15 polyethylene, polypropylene, and copolymers such as ethylene vinylacetate (EVA), ethylene methyl acrylate (EMA) and ethylene acrylic acid (EAA), or blends of such polyolefins. The olefins that may be polymerized alone or in admixture with other ethylenically

20 unsaturated monomers include, e.g., ethylene; propylene; 1-butene; isobutene; 1-pentene; halogenated olefins such as chloroprene; vinyl benzenes and naphthalenes such as styrene or vinyl naphthalene; vinyl or vinylidene halides such as vinyl chloride and

25 vinylidene chloride; vinyl esters such as vinyl acetate

- 10 -

and vinyl benzoate; acrylic and methacrylic acids
(otherwise known as polyacrylate or methacrylate) and
esters or amides thereof; and dienes such as butadiene,
isoprene and cyclopentadiene. Other examples of
5 polymers suitable for use as films in the composite
sheet of this invention are known and referenced in
relevant patents regarding extrusion lamination of
nonwoven webs including U.S. Patent Nos. 2,714,571;
3,058,863; 4,522,203; 4,614,679; 4,692,368; 4,753,840
10 and 5,053,941 herein incorporated by reference.

The web may be a fibrous nonwoven web
comprising fibers of polyethylene, polypropylene,
polyesters, rayon, cellulose, nylon, and blends of such
fibers. A number of definitions have been proposed for
15 nonwoven fibrous webs. The fibers are usually staple
fibers or continuous filaments. As used herein
"nonwoven fibrous web" is used in its generic sense to
define a generally planar structure that is relatively
flat, flexible and porous, and is composed of staple
20 fibers or continuous filaments. For a detailed
description of nonwovens, see "Nonwoven Fabric Primer
and Reference Sampler" by E. A. Vaughn, Association of
the Nonwoven Fabrics Industry, 3d Edition (1992). The
nonwovens may be carded, spun bonded, wet laid, air

- 11 -

laid and melt blown as such products are well known in the trade.

Alternatively, the web may be a woven fabric having elastic qualities which may be imparted to the final laminated product. It is also possible to
5 laminate a polymer web to the extruded polymer to form a multi-layer polymer laminate.

The following examples illustrate the process of making the laminates of the present invention and the processing machinery used in such methods. In
10 light of these examples and this further detailed description, it is apparent to a person of ordinary skill in the art that variations thereof may be made without departing from the scope of this invention.

15 Example 1

A carded polypropylene nonwoven fibrous web of 26 g/yd² density is loaded into the unwind position. The wide web is then fed through the zero speed thermal splicer and festoon and slit into a plurality of
20 adjacent narrow webs. At a line speed of 500 FPM the narrow webs are then spaced apart by being turned about the spaced turning bars. The web guides then steer the narrow webs to the laminating station where the webs are laminated by extrusion of an LDPE thermoplastic
25 film with a density of 0.914 g/cc at 1 mil. The LDPE

- 12 -

film is extruded through a die at about 625°F. and into the nip rollers which press on the webs and LDPE film at about 30 psi. The LDPE thermoplastic film is then slit and folded back upon itself and wound around the winder for storage or later use.

Example 2

In this Example the same procedures are followed as in Example 1, except the plastic used for extrusion is DOW Chemical elastomer incite resin XU51800.51 with a density of 0.870 grams per cubic centimeter.

Example 3

A carded polypropylene having a density of 34 grams/yd² is loaded, slit and separated as in example 1, but at a line speed of about 1000 FPM, and coated with EVA copolymer at about 1.0 mil. The EVA film is extruded through a die at 500°F and into the nip rollers which press on the webs and EVA film at 80 psi.

Example 4

A carded polypropylene nonwoven having a density of 34 g/yd² is loaded, slit and separated as in example 1, but at a line speed of about 750 FPM, and coated with EVA copolymer at about 2.0 mils. The EVA film is extruded through a die at 570°F and into the

- 13 -

nip rollers which press on the webs and EVA film at 10 psi.

Example 5

5 A carded polypropylene nonwoven having a density of 41 g/yd² is extrusion laminated with 2 mil of EPDM elastomer at a line speed of about 850 FPM. The EPDM film is extruded through a die at about 540°F and into the nip rollers which press on the webs and EVA film at about 40 psi.

10 Example 6

DU PONT SONTARA polyester fabric grade 8000 is extrusion laminated to 1 mil of DU PONT polyester elastomer (HYTREL 8260) at a line speed of about 950 FPM. The HYTREL film is extruded through a die at about 580°F and into the nip rollers which press on the webs and HYTREL film at about 60 psi.

Example 7

20 EXXON EXACT polymer type 4011 of ethylene and octene manufactured by using a Metallocene catalyst a density of 0.885 g/cc extrusion laminated to DU PONT's polyester SONTARA fabric grade 8000 at a line speed of about 700 FPM. The EXACT film is extruded through a die at about 530°F and into the nip rollers which press on the webs and EVA film at about 50 psi.

- 14 -

Example 8

A carded polypropylene nonwoven fibrous web of 20 grams/yd² is loaded into the unwind position. The wide web of this nonwoven roll is then fed through the
5 slitting station to form multiple adjacent webs approximately 14 inches wide. Each 14 inch wide web is then folded approximately 3.5 inches from the free edges of slit nonwoven toward the center of the nonwoven, so that both edges abut one another. The
10 folded nonwoven webs are steered to the desired spacing to each other, i.e., 0.25 inch wide by spaced turning bars which are controlled by web guides. The spaced and folded nonwoven webs are then fed to an extrusion laminating station and laminated by extrusion of a
15 polyethylene film of 0.914 grams/cm³. This polyethylene film having a thickness of approximately 0.8 mils is extruded through a conventional extrusion die, at a melt temperature between 400°-600°F, into the nip rollers which press on the webs and polyethylene film
20 with approximately 30-60 psi of pressure to achieve the desired bond strength of between 10 grams/inch to several hundred grams/inch of peel strength.

The laminate then enters a slitting station where slitting knives are located between the folded
25 nonwoven webs to slit the polyethylene film.

- 15 -

Accordingly, the 7 inch folded nonwoven webs are all laminated to polyethylene film of 7.25 inches wide. The 7 inch nonwoven web is laminated with polyethylene film with a 0.125 inch wide loose flap of polyethylene film on each side of the nonwoven which is not laminated to nonwoven. The strip laminated, folded nonwoven is wound directly onto a roll for storage or later use.

Example 9

The non-woven is slit and folded as in Example 8. However, the spacing between each folded web is adjusted to approximately 4" wide. The slitting knives are located between adjacent folded nonwoven webs to split the polymer into 11 inch widths. The result is a nonwoven web of 14" width which is covered with an 11 inch wide polymeric film where 7 inch width of this film is laminated to the 7 inches at the center of the folded nonwoven. The additional polyethylene film of 2" on opposite sides of the laminated nonwoven, which is not laminated to the nonwoven web, may be used to construct barrier cuffs to provide a self-contained pocket to confine body waste.

- 16 -

Example 10

A carded polypropylene nonwoven fibrous web of 20 grams/yd² is loaded into the unwind position. The wide web of this nonwoven roll is then fed through a
5 slitting station to form multiple adjacent webs approximately 14 inches wide. Each 14 inch wide web is then folded approximately 3.5 inches from the free edges of slit nonwoven toward the center of the nonwoven, so that both edges abut one another. This 7
10 inch wide web is the folded a second time approximately 1.75 inches from the outer edge so that the folded edges abut one another. The folded nonwoven webs are then steered to the desired spacing to each other, i.e., 0.25 inches, by spaced turning bars which are
15 controlled by web guides. The spaced and folded nonwoven webs are then fed into the extrusion laminating station and laminated by extrusion of a polyethylene film of 0.914 grams/cm³. This polyethylene film of approximately 0.8 mils is extruded through a
20 conventional extrusion die, at a melt temperature between 400°-600°F, into the nip rollers which press on the webs and polyethylene film with approximately 30-60 psi of pressure to achieve the desired bond strength of between 10 grams/inch to several hundred grams/inch of
25 peel strength.

- 17 -

The laminate then enters a slitting station where slitting knives are located between the folded nonwoven webs to slit the polyethylene film.

Accordingly, the 3.5 inch folded nonwoven webs are all laminated to polyethylene film of 3.75" wide. The 3.5 inch wide folded nonwoven web is laminated with polyethylene film with a 0.125 inch wide loose flap of polyethylene film on each side of the nonwoven which is not laminated to nonwoven.

The strip laminated, folded nonwoven is then unfolded and wound onto a roll for storage or later use.

Example 11

The non-woven is slit and folded as in Example 10. However, the spacing between each folded web is adjusted to approximately 2 inches wide. The knives are located between adjacent folded nonwoven webs to slit the polymer into 11 inch widths. The result is a nonwoven web of 14 inch width is covered with a 5.5 inch wide polymeric film where 3.5 inches width of this film is laminated to the 3.5 wide folded nonwoven at the center of the web. The additional polyethylene film of 1" on opposite sides of the laminated nonwoven, which is not laminated to the

- 18 -

nonwoven web, may be used to construct barrier cuffs to provide a self-contained pocket to confine body waste.

Example 13

A carded polypropylene nonwoven fibrous web
5 of 20 grams/yd² is loaded into the unwind position. A
roll of polypropylene film is loaded into a second unwind
position. The polymer is unrolled and fed through a
slitting station to form a multiple adjacent strips of
polypropylene approximately 7 inches wide. The strips
10 of polypropylene are then separated, by approximately 7
inches, by spaced turning bars which are controlled by
web guides. The wide nonwoven web is then fed to the
laminating station and laminated by patterned pressure
rollers to the spaced strips of polypropylene film at a
15 pressure to achieve the desired bond strength anywhere
between 10 grams/inch to several hundred grams/inch of
peel strength.

The laminate then enters a slitting station
where slitting knives are located between the strips of
20 polyethylene film to slit the nonwoven material. The
result is 14 inch wide nonwoven webs laminated to
polyethylene film of 7 inches wide located at the
center of the nonwoven strip.

- 19 -

Example 14

A carded polypropylene nonwoven fibrous web of 20 grams/yd² is loaded into the unwind position. The wide web of this nonwoven roll is then fed through the
5 slitting station to form multiple adjacent webs approximately 11 inches wide. Each 14 inch wide web is then folded approximately 2 inches from the free edges of slit nonwoven toward the center of the nonwoven. The folded nonwoven webs are steered to the desired
10 spacing to each other, i.e., 7 inches wide, by spaced turning bars which are controlled by web guides. The spaced and folded nonwoven webs are then fed to an extrusion laminating station and laminated by extrusion of a polyethylene film of 0.914 grams/cm³. This
15 polyethylene film having a thickness of approximately 0.8 mils is extruded through a conventional extrusion die, at a melt temperature between 400°-600°F, into the nip rollers which press on the webs and polyethylene film with approximately 30-60 psi of pressure to
20 achieve the desired bond strength of between 10 grams/inch to several hundred grams/inch of peel strength.

The laminate then enters a slitting station where slitting knives are located between the folded
25 nonwoven webs to slit the polyethylene film.

- 20 -

Accordingly, the 7 inch folded nonwoven webs are all laminated to polyethylene film of 14 inches wide. The 7 inch nonwoven web is laminated with polyethylene film with a 3.5 inch wide loose flap of polyethylene film on each side of the nonwoven which is not laminated to nonwoven. The strip laminated, folded nonwoven is wound directly onto a roll for storage or later use. The product of example 6 may be used as a polymer back-sheet of a diaper with the folded portion of the nonwoven forming a 2 inch standing leg cuff.

In Examples 1-15, the polyethylene film may be replaced by a microporous formable film composed of 30% to 40% polyethylene, 10%-15% of poly(ethylene-vinylacetate) copolymer, 40%-55% of stearic acid treated calcium carbonate and 5%-10% of glycerol monostearate. This nonwoven web with a center portion of the nonwoven laminated to the above microporous formable film can be interdigitately stretched on its CD and/or MD directions in the center portion of laminated area to form a microporous laminate in the center portion of this nonwoven web. The product accordingly is a fluid barrier in the center portion but is breathable to air, moisture, and moisture vapor due to its high degree of microporosity. The method of stretching is detailed in U.S. Patent Nos. 5,296,184;

- 21 -

5,254,111 and 5,202,173 herein incorporated by reference in their entirety.

In a preferred form, the laminated sheet employs a thermoplastic film having a gauge or a thickness between about 0.25 and 10 mils and, depending upon use, the film thickness will vary and, most preferably, in disposable applications is on the order of about 0.25 to 2 mils in thickness. The nonwoven fibrous webs of the laminated sheet normally have a weight of about 10 grams per square yard to 60 grams per square yard preferably about 20 to about 40 grams per square yard. As indicated above, the composite or laminate may be used in many different applications such as baby diapers, baby training pants, catamenial pads, garments, and the like.

The present invention allows a continuous in-line process for introducing the web material to the laminator, for embossing and laminating strips or zones of polymer to non-woven in-line with high efficiency. For simplicity, extrusion laminating and dynamic mechanical bonding are shown in the figures and fully described in the specification, however, there are other possible laminating steps including adhesive laminating, spray laminating, gravure laminating, slot

- 22 -

die laminating, ultrasonic laminating or thermal bond laminating.

As shown in FIG. 1, two rolls of nonwoven fibrous sheets 2, 3 of 5-70 grams per square yard may be loaded into the two position unwind station 1. The sheet 4 is unwound and fed into the apparatus. The end of a first roll 2 may be spliced to the beginning of the second roll 3 by a zero speed thermal splicer 5. Alternatively, the splice may be a zero speed tape splice or a flying tape splice. The sheet 4 engages a festoon 6 if a zero speed splice is desired. The sheet 4 is then slit by slitteer 8 into narrow webs 9. The narrow webs 9 are adjacent after slitting. The narrow webs 9 are subsequently spaced apart by turning apparatus and web guides which are sequentially spaced down the longitudinal axes of the incoming narrow webs 9. By controlling the separation of the web slitters, it is possible to obtain laminates having different web widths, different final laminant widths, and unequal polymer overhang from each side of the narrow web.

The turning apparatus is preferably a series of turning bars 12 which lie in the plane of the incoming narrow webs 9. The webs are guided to the embossing and laminating station 15 by way of web guides 12. The web guides 12, shown in detail in FIG.

- 23 -

3, include an edge sensor 56 which optically senses the lateral deviation of the narrow web 9. The turning bar 10 is fixed to a mounting plate 54 by linear bearings 50. The edge sensor 56 is linked to actuator 52. Based upon a signal emitted from edge sensor 56, the actuator 52 moves the turning bar laterally on the linear bearings to compensate for any deviation of the narrow web 9. Embossing and laminating station 15 includes rollers 14, 16, an extruder 20 and a die 18 for extruding a sheet of polymer film 19 onto the narrow webs 9. The polymer film 19 and the narrow webs 9 are jointed at the nip of rollers 14 and 16. The polymer layer 19 is extruded from the die 18 at a temperature of about 500 to 625°. The extruded polymer film 19 is on the order of about 0.25 to 8 mils in thickness and is laminated at temperatures on the order of about 500 to 625°. The compressive force at the nip is controlled such that the webs are bonded to the polymer film. Pressures on the order of about 40 to 200 pli (pounds per linear inch) are sufficient to achieve satisfactory bond for fibrous webs of about 5-70 grams per square yard. The resulting laminate 21 of polymer film 19 and nonwoven webs 9 is then tensioned between spaced rollers 22 and 24 so that the laminate may be slit by blades 26 to form individual laminate webs 28.

- 24 -

The laminate webs 28 include a single web of nonwoven, woven or polymer material with a polymer layer adhered to one side of the web and overhanging the edges of the web. The overhanging edges may then be folded back to produce a laminated layer the width of the nonwoven web 9 with a polymer film 19 adhered to one side. The narrow laminated webs 28 may then be wound on a winder 30 for storage or future use.

As shown in FIG. 2, two rolls of nonwoven fibrous sheets 2, 3 of 5-70 grams per square yard may be loaded into the two position unwind station 1. The sheet 4 is unwound and fed into the apparatus. The end of a first roll 2 may be spliced to the beginning of the second roll 3 by a zero speed thermal splicer (as shown in FIG. 1). Alternatively, the splice may be a zero speed tape splice or a flying tape splice. The sheet 4 will engage a festoon if a zero speed splice is desired. The sheet 4 is then slit by slit 8 into narrow webs 9. The narrow webs are adjacent after slitting. The narrow webs 9 are subsequently folded by folding apparatus 13 to form folded webs 9A and separated by a predetermined distance by turning apparatus 12 and web guides 56 which are sequentially spaced down the longitudinal axes of the incoming folded webs 9A. By controlling the separation of the

- 25 -

web slitters, it is possible to obtain laminates having different web widths, different final laminant widths, and unequal polymer overhang from each side of the folded webs 9A.

5 The turning apparatus is preferably a series of turning bars 10 which lie in the planes of the incoming folded webs 9A. As discussed above with reference to FIG. 3, the webs are guided to the embossing and laminating station 15 by way of web guides 56. The web guides 56, shown in detail in FIG. 10 2, include an edge sensor 56a which optically senses the lateral deviation of the folded web 9. The turning bar 10 is fixed to a mounting plate 54 by linear bearings 50. The edge sensor 56a is linked to actuator 15 52. Based upon a signal emitted from edge sensor 56a, the actuator 52 moves the turning bar 10 laterally on the linear bearings to compensate for any deviation of the folded web 9. Embossing and laminating station 15 includes rollers 14, 16 an extruder 20 and a die 18 for 20 extruding a sheet of polymer film 19 onto the folded web 9A. The polymer film 19 and the folded webs 9A are jointed at the nip of rollers 14 and 16. The polymer layer 19 is extruded from the die 18 at a temperature of about 350° to 625°. The extruded polymer film 19 is 25 on the order of about 0.25 to 8 mils in thickness and

- 26 -

is laminated at temperatures on the order of about 350° to 625°. The compressive force at the nip is controlled such that the webs are bonded to the polymer film. Pressures on the order of about 40 to 200 pli (pounds per linear inch) are sufficient to achieve satisfactory bond for fibrous webs of about 5-70 grams per square yard. The resulting laminate 21 of polymer film 19 and folded nonwoven webs 9A is then tensioned between spaced rollers 22 and 24 so that the laminate may be slit by blades 26 to form individual laminate webs 28 which are wound on winder 30.

The laminated webs 28 of polymer and nonwoven are shown in FIG. 6 prior to slitting and a single web, after slitting is shown in FIG. 7.

A second embodiment of the present invention is shown in FIG 2A. The incoming narrow web 9 is folded by a first folding apparatus 13 to form folded web 9A, which may approach approximately one half of the width of narrow web 9. The folded webs 9A are then folded by second folding apparatus 13A to form double folded web 9B, which may approach approximately one quarter the width of narrow web 9. The folding and unfolding apparatus 13 are shown in detail in figures 4, 5, and 8. After leaving the slitter 8 narrow webs 9 contact a folding guide 60 and folding bar 64. Folding

- 27 -

guide 60 is supported on support bar 62. Folding plate 64 is supported by folding plate support 66, shown cut-away for clarity. Folding plate support 66 extends along the longitudinal direction of the folding plate 64 and may serve as a guide to prevent overlapping of the free edges of the narrow web.

In FIG. 4 the incoming narrow web 9, shown in phantom, contacts the inner portion 60A of the folding guide 60. The lateral edges of the narrow web follow the contour of guide 60 and move up and over folding bar 64. The trailing portion 60B of folding guide 60 forces the free edges of narrow web 9 against folding bar 64.

Prior to rolling the laminate 28 on winder 30 the folded nonwoven may be unfolded by unfolding bar 68, as shown in FIG. 5. During unfolding, folded web 9A of the incoming laminate 28 contacts unfolding bar. As the opposing flaps of the folded nonwoven 9A run along the increasing width of the unfolding bar the nonwoven material is unfolded. FIG. 5 also shows the loose polymer overhang 19A, both shown in phantom for clarity, of the extruded polymer 19.

The material produced by the present invention includes a wide section of nonwoven 9 which is extrusion laminated to a polymer film. FIG. 6 shows

- 28 -

two strips of folded nonwoven material 9A laminated to polymer film 19. The final product 28, after slitting and unfolding, is shown in FIG. 7. The final product includes a strip of nonwoven 9 laminated to a portion
5 of the polymer film 19B with loose polymer flaps 19A on either side of the laminated portion 19B.

Another embodiment of the present invention is shown in FIG. 9. A roll 102 of nonwoven fibrous sheet 104 is loaded into the unwind position 101. The
10 end of roll 102 may be spliced to the beginning of a second roll (not shown) by a zero speed splice or a flying splice. If a zero speed splice is to be used, the web 104 should engage a festoon 6 (as shown in FIG. 1). A roll of a sheet of polymer film 119 is loaded
15 into a second unwind position 118. The end of the sheet of polymer film 119 may be spliced to another roll by a zero speed or flying splice, as discussed above. As an alternative the sheet of polymer film 119 may be extruded through an extruder 20 (as shown in
20 FIG. 1). The edges of the extruded film would be trimmed to proper size prior to or at slitting station 108. The polymer is unrolled and fed through a slitting station 108 to form multiple adjacent strips of polymer 106. The strips of polymer 106 are then
25 separated by a predetermined distance by spaced turning

- 29 -

bars 112 which are controlled by web guides 156. The turning bars 112 are similar to those shown in FIG. 3. The wide nonwoven web 104 is then fed to the laminating station 115 and laminated by heated pressure rollers 114 and 116 to the spaced strips of polymer film 106 at a pressure to achieve the desired bond strength.

The laminate then enters a slitting station 126 where slitting knives are located between the strips of polymer film to slit the nonwoven material. The resultant nonwoven webs are laminated to polymer film at the center of the nonwoven strip. The final product 128 is wound on take-up reel at winder station 130. This product is similar to that shown in FIG 6, however there are no loose polymer flaps 19A at the outer edges of the laminated portion 19B.

While the invention has been described with reference to specific embodiments and examples herein, it is not intended that the invention be limited to such specifics. Various exchanges and modifications may occur to persons skilled in the art which are within the scope of the invention as defined in the appended claims.

- 30 -

What is claimed is:

1. An apparatus for in-line lamination of a first sheet and a second sheet, comprising:

a web slitter for dividing said first sheet into a plurality of narrow webs;

5 a plurality of spaced turning means for turning each of said narrow webs such that the plurality of webs are separated by a predetermined distance; and

10 a laminator for laminating said second sheet on a surface of the separated webs to provide a laminate of said second sheet and the separated webs and having a portion of the second sheet between the webs.

- 31 -

2. The apparatus of claim 1 wherein said first sheet is a nonwoven web and said second sheet is a polymer film.
3. The apparatus of claim 2 further comprising:
an extrusion die for forming said polymer film.
4. The apparatus of claim 1 wherein said first sheet is a polymer film and said second sheet is a nonwoven web.
5. The apparatus of claim 1 further comprising:
a first plurality of folding means for folding each narrow web.
6. The apparatus of claim 5 further comprising:
a second plurality of folding means for folding the folded web output from the first plurality of folding means.
7. The apparatus of claim 5 further comprising:
a plurality of unfolders, located downstream from said laminator, for unfolding the narrow webs.

- 32 -

8. The apparatus of claim 1 wherein said predetermined distance spacing between the folded webs is sufficient to form a standing leg cuff of an under garment.

9. The apparatus of claim 1 wherein said laminator is selected from the group consisting of an extrusion laminator, adhesive laminator, spray laminator, gravure laminator, slot die laminator, ultrasonic laminator, thermal bond laminator, and dynamic mechanical laminator.

10. The apparatus of claim 1 wherein said turning means are equally spaced.

11. The apparatus of claim 1 wherein said turning means are unequally spaced.

12. The apparatus of claim 1 further comprising:
means for slitting the film layer
between the separated webs.

13. The apparatus of claim 12 wherein said means for slitting is selected from the group consisting of a

- 33 -

score slitter, shear slitter, razor slitter, water jet slitter and ultrasonic slitter.

14. The apparatus of claim 1 further comprising:

an unwind station for storing at least one roll of the wide web.

15. The apparatus of claim 14 further comprising wherein said unwind station is a two position unwind station.

16. The apparatus of claim 1 further comprising:

an automatic splicing means.

17. The apparatus of claim 16 wherein said automatic splicing means is selected from the group consisting essentially of zero speed thermal splicer, zero speed tape splicer or flying tape splicer.

18. The apparatus of claim 1 wherein said turning means include means for guiding the plurality of webs from said spaced turning mechanism to said laminator.

19. The apparatus of claim 1 further comprising:

- 34 -

a take-up reel for receiving the
laminated web and film.

- 35 -

20. A process for in-line lamination of a first sheet to a second sheet by the steps of:

slitting a first sheet to form a plurality of narrow webs;

5 spacing the narrow webs by turning said webs around a plurality of spaced web turners;

10 laminating a second sheet onto a surface of the spaced webs to provide a laminate of the second sheet and the spaced webs having a portion of said second sheet between the spaced narrow webs of the first sheet.

21. The process of claim 20 further comprising the step of:

folding each narrow web prior to said laminating step.

22. The process of claim 20 wherein said laminating step is performed by a laminator selected from the group consisting of an extrusion laminator, adhesive laminator, spray laminator, gravure laminator, slot die laminator, ultrasonic laminator, thermal bond laminator, and dynamic mechanical laminator.

- 36 -

23. The process of claim 20 further comprising the step of:

slitting the portion of the second sheet between the separated webs.

24. The process of claim 20 wherein said slitting step is performed by a slitter selected from the group consisting of a score slitter, shear slitter, razor slitter, water jet slitter and ultrasonic slitter.

25. The process of claim 20 further comprising the step of:

winding at least one roll of the laminated first and second sheets.

26. The process of claim 20 further comprising the step of:

automatically splicing the end of a first roll of sheet material to the start of a second roll of sheet material.

27. The process of claim 26 wherein said automatic splicing step is selected from the group consisting essentially of zero speed thermal splicing, zero speed tape splicing or flying tape splicing.

- 37 -

28. The process of claim 20 wherein said turning step also includes a guiding step.

29. The process of claim 20 wherein said first sheet comprises polyolefin fibers.

30. The process of claim 20 wherein said second sheet is a polyolefin film.

31. The process of claim 20 wherein said first sheet is selected from the group consisting of polypropylene, polyethylene, polyesters, cellulose, rayon, nylon and blends of two or more of such fibers.

32. The process of claim 20 wherein said second sheet is selected from the group consisting of polyethylene, polypropylene and copolymers thereof.

33. The process of claim 20 wherein said first sheet has a weight from about 5 to 70 grams/yd² and second sheet has a film thickness of about 0.25 to about 10 mils and the inline laminating is conducted at about 500 to about 1000 fpm.

- 38 -

34. The process of claim 20 wherein said second sheet comprises an elastomeric polymer.

35. The process of claim 34 wherein the elastomeric polymer is selected from the group consisting of poly(ethylene-butene), poly(ethylene-hexene), poly(ethylene-octene), poly(ethylene-propylene),
5 poly(styrene-butadiene-styrene), poly(styrene-isoprene-styrene), poly(styrene-ethylene-butylene-styrene), poly(ester-ether), poly(ether-amide) poly(ethylene-vinylacetate), poly(ethylene-methylacrylate), poly(ethylene-acrylic acid), poly(ethylene-
10 butylacrylate), polyurethane; poly(ethylene-propylene-diene), and ethylene-propylene rubber.

36. The process of claim 20 wherein said second sheet has a thickness on the order of about 0.25 to about 10 mils.

37. The process of claim 20 wherein said second sheet is a polyolefin derived from the polymerization of monomers selected from the group consisting of ethylene, propylene, styrene, butene, hexene and octene, and mixtures thereof.

- 39 -

38. An apparatus for separating a plurality of adjacent webs comprising:

a plurality of turning bars positioned at an angle to the longitudinal axes of the webs and separated by a predetermined distance along the longitudinal axes of the webs.

- 40 -

39. The apparatus of claim 38 further comprising:
means for guiding the plurality of webs
from said turning bars.
40. The apparatus of claim 38 wherein said turning
bars are equally spaced.
41. The apparatus of claim 38 wherein said turning
bars are unequally spaced.

- 41 -

42. A method of separating adjacent webs from sheet material comprising the step of:

5 turning the webs around a plurality of parallel turning bars positioned at an angle to the longitudinal axes of the webs and separated by a predetermined distance along the longitudinal axes of the webs.

- 42 -

43. The method of claim 42 wherein said turning bars are equally spaced.

44. The method of claim 42 wherein said turning bars are unequally spaced.

- 43 -

45. The product formed by the process of in-line lamination of a first sheet to a second sheet by the steps of:

slitting a first sheet to form a plurality of narrow webs;

spacing the narrow webs by turning said webs around a plurality of spaced turning means;

laminating a second sheet onto a surface of the spaced webs to provide a laminate of the second sheet and the separated webs having a portion of said second sheet therebetween.

- 44 -

46. The product formed by the process of claim 45 wherein said first sheet is a polymer film and said second sheet is a nonwoven web.

47. The product formed by the process of claim 45 wherein said first sheet is a nonwoven web and said second sheet is a polymer film.

48. The product formed by the process of claim 47 further comprising the step of:
folding the narrow webs.

49. The product formed by the process of claim 45 wherein the said laminating step is performed by a laminator selected from the group consisting of an extrusion laminator, adhesive laminator, spray laminator, gravure laminator, slot die laminator, ultrasonic laminator, thermal bond laminator and dynamic bond laminator.

50. The product formed by the process of claim 45 wherein said predetermined spacing between the folded webs is sufficient to form a standing leg cuff.

- 45 -

51. The product formed by the process of claim 46 further comprising:

the step of slitting the film layer between the separated folded webs.

52. The product formed by the process of claim 46 wherein one of said sheets comprises polyolefin fibers.

53. The product formed by the process of claim 46 wherein one of said sheets is a polyolefin film.

54. The product formed by the process of claim 46 wherein one of said sheets is selected from the group consisting of polypropylene, polyethylene, polyesters, cellulose, rayon, nylon and blends of two or more of such fibers.

55. The product formed by the process of claim 45 wherein the thermoplastic film is selected from the group consisting of polyethylene, polypropylene and copolymers thereof.

56. The product formed by the process of claim 45 wherein the nonwoven web has a weight from about 5 to 70 grams/yd² and the thermoplastic film has a film

- 46 -

thickness of about 0.25 to about 10 mils and the in-line laminating is conducted at about 500 to about 1000 fpm.

57. The product formed by the process of claim 45 wherein the thermoplastic film comprises an elastomeric polymer.

58. The product formed by the process of claim 54 wherein the elastomeric polymer is selected from the group consisting of poly(ethylene-butene), poly(ethylene-hexene), poly(ethylene-octene),
5 poly(ethylene-propylene), poly(styrene-butadiene-styrene), poly(styrene-isoprene-styrene), poly(styrene-ethylene-butylene-styrene), poly(ester-ether), poly(ether-amide) poly(ethylene-vinylacetate), poly(ethylene-methylacrylate), poly(ethylene-acrylic
10 acid), poly(ethylene-butylacrylate), polyurethane; poly(ethylene-propylene-diene), and ethylene-propylene rubber.

59. The product formed by the process of claim 45 wherein said film has a thickness on the order of about 0.25 to about 10 mils.

- 47 -

60. The product formed by the process of claim 45 wherein the polymer film is a polyolefin derived from the polymerization of monomers selected from the group consisting of ethylene, propylene, styrene, butene, hexene and octene, and mixtures thereof.




FIG. 1

2/7




FIG. 2

3/7










FIG. 2A

4/7





6/7



7/7




FIG. 9

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 96/17165

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 B32B3/14 B65H23/035 B65H23/32 B65H35/02 B29C53/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 A61F B65H B32B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 008, no. 182 (M-319), 22 August 1984 & JP,A,59 074848 (KONISHIROKU SHASHIN KOGYO KK), 27 April 1984, see abstract	38-44
Y	---	1-37, 45-60
Y	US,A,2 897 108 (HARWOOD) 28 July 1959 see the whole document	1-37, 45-60
X	---	38-44
	EP,A,0 316 875 (ASHTON M A N INC) 24 May 1989 see abstract; figure 1 ---	
	-/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubt on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

A document member of the same patent family

Date of the actual completion of the international search

24 January 1997

Date of mailing of the international search report

18. 02. 97

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Lanaspeze, J

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 96/17165

C (Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	GB,A,2 193 734 (ORBIT WEAVING MACHINERY LIMITE) 17 February 1988 see abstract; figures ---	5-7,21, 48
A	GB,A,2 154 494 (GD SPA) 11 September 1985 see abstract; figure 1 ---	18,28,39
A	FR,A,2 209 520 (LABAZ) 5 July 1974 see the whole document ---	1,20,45
A	WO,A,95 00092 (PROCTER & GAMBLE) 5 January 1995 see abstract; figures 3,4 ---	1,20,45
A	US,A,4 915 282 (MARTIN JOHN R ET AL) 10 April 1990 see abstract; figure 1 -----	16,17, 26,27

INTERNATIONAL SEARCH REPORT

Inter- national Application No
PCT/US 96/17165

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-2897108	28-07-59	GB-A- 748628	
EP-A-0316875	24-05-89	US-A- 4811880	14-03-89
		CA-A- 1310346	17-11-92
GB-A-2193734	17-02-88	NONE	
GB-A-2154494	11-09-85	DE-A- 3502009	05-09-85
		FR-A- 2560176	30-08-85
		JP-C- 1866378	26-08-94
		JP-A- 60188052	25-09-85
		US-A- 4627319	09-12-86
FR-A-2209520	05-07-74	NONE	
WO-A-9500092	05-01-95	AU-A- 7102994	17-01-95
		EP-A- 0706359	17-04-96
		JP-T- 8511705	10-12-96
		US-A- 5567260	22-10-96
US-A-4915282	10-04-90	NONE	

This Page Blank (uspto)